



Peerless of America^{II}
Since 1912

Peerless "Peerlite" Coating

A flexible dip and bake epoxy coating

Color:	Black
Coating Thickness:	.08 – 1.0 Mil (20.3 – 30.5 Microns)
Effect on Heat Transfer:	Less than 1%
Thermal Expansion:	-50F deg to 450F deg
Elongation:	200%
Salt Spray:	3000 + hours

**Meets military specification Mil-P-53084
NSF Approved**

Chemical Resistance Chart

Acetone		Formaldehyde 27%		Phosgene	
Acetic Acid	98%	Formic Acid	88%(NR)	Phenolphthalein	
Acetates	(all)	Fructose		Phosphoric Acid	
Amines	(all)	Gasoline		Potassium Chloride	
Ammonia		Glucose		Potassium Hydroxide	
Ammonium Hydroxide		Glycol Ether		Propionic Acid	
Amino Acids		Hydrochloric Acid	37%	Propyl Alcohol	
Benzene		Hydrofluoric Acid	30%	Propylene Glycol	
Borax		Hydrogen Peroxide	5%	Salicylic Acid	
Boric Acid		Hydrogen Sulfide		Salt Water	
Butyl Alcohol		Iodine		Sodium Bisulfite	
Butyl Cellosolve		Isobutyl Alcohol		Sodium Chloride	
Butric Acid		Isopropyl Alcohol		Sodium Hypochlorite	5%
Calcium Chloride		Kerosene		Sodium Hydroxide	10%
Calcium Hypochlorite		Lactic Acid		Sodium Hydroxide	25%
Carbon Tetrachloride		Lactose		Sodium Sulfate	
Cetyl Alcohol		Lauryl Alcohol		Stearic Acid	
Chlorides	(all)	Magnesium Chloride		Sulfuric Acid	25 - 85%
Chlorine Gas		Magnesium Sulfate		Sulfates	(all)
Chloroform		Maleic Acid		Sulfides	(all)
Chromic Acid	25%	Menthanol		Sulfites	(all)
Citric Acid		Methylene Chloride		Toluene	
Cresol		Methyl Ethyl Ketone		Triethanolamine	
Diesel Fuel		Naphthol		Urea	
Diethanolamine		Nitric Acid	25%	Vinegar	
Ethyl Acetate		Nitric Acid	60%(NR)	Xylene	
Ethyl Alcohol		Oxalic Acid			
Fatty Acid		Perchloric Acid			
Fluorine Gas		Phenol	85%		

(NR) = Not Recommended

Phone: (217) 342-0424 Fax: (217) 342-0412 E-mail: sales@peerlessofamerica.com

Web Site: www.peerlessofamerica.com



Peerless of America^{II}
Since 1912

Product Comparison

	Peerless Peerlite Coating	Baked Phenol
Color	Black	Brown
Salt Spray	3000 Hours	3000 Hours
Durability	Very Flexible Consistent film	Very brittle Inconsistent film
Heat Transfer Reduction	Less than 1%	2 – 5%
Fin Coverage	100% Guaranteed	Inconsistent
Bridging	0% Guaranteed	Limited to 14 fpi @ 203 mils dft
PH Range	3 - 12	3 - 8

Coating Procedure

140°F alkaline cleaner by immersion

Portable water rinse by immersion

DI water rinse by immersion

Coating tank

Permeate rinse by immersion

Permeate rinse by immersion

350°F oven bake

Phone: (217) 342-0424 Fax: (217) 342-0412 E-mail: sales@peerlessofamerica.com

Web Site: www.peerlessofamerica.com